



GENERAL PRODUCT SPECIFICATION

Item No.	SPC150-P
-----------------	-----------------

Date	16-6-2017	Replaces	18-11-14	No. Pages	1
-------------	-----------	-----------------	----------	------------------	---

Product Description:

Style	Blanket roll, high strength perforation every 44 cm for single or multiple/variable length pads
Item Size (each)	96 cm wide by 44 m long (100 Pads)
Color	White
Composition	100% Polypropylene
Structure	Nonwoven mat of randomly oriented Micro-fibers [4-10 micron diameters]
Technology	Meltblown, 1-ply
Absorbency	Hydrophobic + Oleophilic
Bonding	Mechanical entanglement, dimpled (no Spunbound)

Intended Application	“Half-Size” Chemical Resistant Sorbent BLANKETS for Oil & Solvent Base Liquids.
-----------------------------	--

Absorbency Capacity	231 l per bale (saturated; medium viscosity-13.5x)
----------------------------	--

Packaging Description:

Package configuration	Bale	Pkg. Weight	14.9 kg (14.8 kg)
Items per Package	1-Blanket Roll/Bale	Pkg. Dimensions	43 cm x 43 cm x 98 cm (H)
Container type	Polybag + Twist-Tie		

Physical Properties;

Parameter	SPC Test Method	Units	Nominal	(+/-)Tolerance
Basis Weight	SPCTM-002	G/M2	350	35
Caliper	SPCTM-020	mm	5.3	0.5
Absorbency** (med.visc.)	SPCTM-004B	gL/gS	13.5	2
Tensile Strength	SPCTM-007	daN	8.6	0.8
Color	Visual	-----	White	per standard

The above properties are “nominal” values used for PROCESS CONTROL when the product is produced and/or inspected. Performance “nominals” may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.

**** The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.**

Attributes	Product will be free of foreign material contamination, rips, holes, and tears.
Labeling	Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
Certification	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.