



**GENERAL PRODUCT SPECIFICATION**

<b>Item No.</b>	<b>UXT330-DP-E</b>
-----------------	--------------------

<b>Date</b>	16-6-2017	<b>Replaces</b>	4-11-11	<b>No. Pages</b>	1
-------------	-----------	-----------------	---------	------------------	---

**Product Description:**

<b>Style</b>	Blanket Roll; high strength perforation down the middle for the 38 cm wide dimension, & cross-wise for the 38 cm long dimension.
<b>Item Size (each)</b>	76 cm wide by 46 m long <b>(240 pads)</b>
<b>Color</b>	Dark Gray
<b>Composition</b>	Polypropylene >98%, Surfactant < 1.0%, color pigment < 1.0 %
<b>Structure</b>	A nonwoven mat where the middle ply is made of randomly oriented Micro-fibers [2-10 micron diameters] and the coverstock layers are lint-resistant & abrasion resistant {controlled porosity} spunbond nonwoven of continuous filaments randomly oriented and thermally point bonded [15-30 micron diameters].
<b>Technology</b>	Meltblown & Spunbond, 3-ply
<b>Absorbency</b>	Universal ( <b>Hydrophilic</b> + Oleophilic)
<b>Bonding</b>	Bonded (staggered pattern) + Mechanical entanglement

<b>Intended Application</b>	Low -Lint Chemical Resistant Sorbent for Water, Oil, or Solvent Base Liquids
-----------------------------	------------------------------------------------------------------------------

<b>Absorbency Capacity</b>	14l per bale (saturated; medium viscosity-12x)
----------------------------	------------------------------------------------

**Packaging Description:**

Package configuration	Case	Pkg. Weight	11.4 kg (10.1kg)
Items per Package	1 Roll / Case 240 pads	Pkg. Dimensions	46 cm x 46 cm x 79 cm (H)
Container type	Carton		

**Physical Properties;**

Parameter	SPC Test Method	Units	Nominal	(+/-)Tolerance
Basis Weight	SPCTM-002A	G/M2	290	29
Caliper	SPCTM-020	mm	4.6	0.4
Absorbency ** (med. Oil)	SPCTM-004B	gL/gS	13.5	2
Tensile Strength	SPCTM-007	daN	30	3
Color	Visual	-----	Dark Gray	per standard

**The above properties are “nominal” values used for PROCESS CONTROL when the product is produced and/or inspected. Performance “nominals” may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.**

**\*\* The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.**

<b>Attributes</b>	Product will be free of foreign material contamination, rips, holes, and tears.
<b>Labeling</b>	Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
<b>Certification</b>	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.