

Product Information Sheet
B-351 Lab
Effective Date: 1/23/19

B-351 TAMPER-EVIDENT VINYL LABEL STOCK

This Product Information Sheet is focused on the suitability of B-351 for laboratory applications. For additional data regarding B-351 performance please refer to B-351 Technical Data Sheet.

Description:

GENERAL

Print Technology: Thermal transfer

Material Type: Vinyl Film

Finish: Matte white

Adhesive: Permanent acrylic

APPLICATIONS

Laboratory identification such as well plates, bottles, vials, test tubes and general lab applications requiring evidence of tampering.

RECOMMENDED RIBBONS

Brady Series R4300

REGULATORY APPROVALS

For information on the Weee-RoHS compliance status for a Brady Product go to one of the following websites:

In Canada: www.bradycanada.ca/weee-rohs

In Europe: www.bradyeurope.com/rohs

In Japan: www.brady.co.jp/products/labelsuse/rohs

All other regions: www.bradyid.com/weee-rohs

SPECIAL FEATURES

Brady B-351 is designed to fracture easily to prevent one-piece removal.

Details:

Note: All values shown are averages and should not be used for specification purposes. Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information.

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	ASTM D1000 -Total (excluding liner)	0.0.071 mm (0.0028 inch)
Adhesion to: -Stainless Steel	ASTM D1000 20 minute dwell 24 hour dwell	Label destroys upon removal after both 20 minutes and 24 hours
-Polypropylene	20 minute dwell 24 hour dwell	Label destroys upon removal after both 20 minutes and 24 hours
-Glass	20 minute dwell 24 hour dwell	Label destroys upon removal after both 20 minutes and 24 hours

PERFORMANCE PROPERTIES	LAB SIMULATED ENVIRONMENT
------------------------	---------------------------

Performance properties tested on B-351 printed with the Brady Series R4300 ribbon. Printed samples were laminated to glass microscope slides, glass test tubes (1.1 cm outer diameter) and polypropylene centrifuge tubes (1.1 cm inner diameter, 1.5 ml capacity) and allowed to dwell 24 hours before exposure to the indicated environments.

ENVIRONMENT	TEST METHOD		TYPICAL RESULTS
High Service Temperature**	30 days at various temperatures		No visible effect at 80°C (121°F). Slight discoloration at 100°C (212°F), but is still functional
Freezer	3 cycles of 16 hours at -70°C (-94°F)/ 8 hours at room temperature	✓ ✓ ✓	Glass test tube Polypropylene centrifuge tube Glass microscope slide
Pressure Cooker (simulate autoclave)	3 cycles of 1 hour in 121°C (250°F) 15 psi pressure cooker/23 hours room temperature	✓ ✗ ◆	Glass test tube Polypropylene centrifuge tube Glass microscope slide
Liquid Nitrogen	3 cycles of 4 hours at -196°C (-320°F)/20 hours at room temperature	✗ ✗ ✗ ✓	Glass test tube Polypropylene centrifuge tube Glass microscope slide Aluminum Foil
Freezer to boiling water	1 hour at -70°C (-94°F) then placed in boiling water 100°C (212°F)	✗ ✗ ✗	Glass test tube Polypropylene centrifuge tube Glass microscope slide
Liquid Nitrogen to boiling water	1 hour at -196°C (-320°F) then placed in boiling water 100°C (212°F) for 10 minutes	✗ ✗ ✗ ✗	Glass test tube Polypropylene centrifuge tube Glass microscope slide Aluminum Foil

** Samples for this testing were placed on glass panels

*** Also tested labels on aluminum foil

✓ Label suitable for application; no visible effect, label remains adhered to test surface

◆ Label may work in application; test results were mixed

✗ Label not recommended for application; label came off either during testing or after test surface was removed from environment.

PERFORMANCE PROPERTIES	CHEMICAL RESISTANCE
------------------------	---------------------

Samples of B-351 were printed with the Brady Series R4300 ribbon. Printed samples were laminated to glass microscope slides and allowed to dwell 24 hours prior to testing. Test conducted at room temperature. Samples were immersed in the test solvent for 15 minutes. The samples were removed and rubbed 10 times with a cotton swab saturated with the test fluid. The rating scale below shows the effect to the quality of the print for each sample.

CHEMICAL REAGENT	SUBJECTIVE OBSERVATION OF VISUAL CHANGE		
	EFFECTS TO LABEL STOCK	EFFECTS TO PRINTED IMAGE	
		WITHOUT RUB	WITH RUB

CHEMICAL REAGENT	SUBJECTIVE OBSERVATION OF VISUAL CHANGE		
	EFFECTS TO LABEL STOCK	EFFECTS TO PRINTED IMAGE	
		WITHOUT RUB	WITH RUB
Ethanol	No visible effect	3	5
Toluene	Label came off test surface	X	X
Isopropanol	Slight adhesive ooze	1	5
Chloroform	Label came off test surface	X	X
Xylene	Label came off test surface	X	X
Dimethylsulfoxide (DMSO)	Label is destroyed	X	X
Methylene Chloride	Label came off test surface	X	X
50% Acetic Acid	No visible effect	1	5
10% Hydrochloric Acid	No visible effect	1	1
10% Sodium Hydroxide	No visible effect	1	1
10% Chlorox Solution	No visible effect	1	1

B-351 is not recommended for use in harsh organic solvents such as toluene, chloroform, xylene, DMSO or methylene chloride

Rating Scale:

- 1=no visible effect
- 2=slight smear or print removal, detectable but minimal smear
- 3=moderate smear or print removal (print still legible)
- 4=severe smear or print removal (print illegible or just barely legible)
- 5=complete print and/or topcoat removal
- NP=print removed prior to rub

Shelf Life:

Shelf life is two years from the date of receipt for this product as long as this product is stored in its original packaging in an environment below 80° F (27° C) and 60% RH. It remains the responsibility of the user to assess the risk of using this product. We encourage customers to develop testing protocols that will qualify a product's fitness for use in their actual application.

References:

- ASTM: American Society for Testing and Materials (U.S.A.)
- All S.I. Units (metric) are mathematically derived from the U.S. Conventional Units
- Note: All values shown are averages and should not be used for specification purposes.

WARRANTY

Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use, Brady's products.